

## 980 nm band PANDA

### Feature

- 980 nm band polarization maintaining fiber

### Common specifications

Mode field diameter	6.6 ± 0.5 μm @ 980 nm
Concentricity error	≤ 0.5 μm
Cladding diameter	125 ± 1 μm (Major diameter)
Attenuation	≤ 2.5 dB/km @ 980 nm
Cutoff wavelength	0.87 – 0.95 μm
Polarization crosstalk	≤ -30 dB/100m @ 980 nm
Beat length	1.5 - 2.7 mm @ 980 nm
Minimum bending radius	1% proof : R30 mm 2% proof : R20 mm*

### Product list

Product*	Coating structure	Coating diameter	Specification number		
			---	ID	Rev
SM98-PS-H90D	UV curable acrylate /Polyester elastomer (Color : Green)	900 ± 100 μm	B-13D0086-6B-	1	0
SM98-PS-H90D-H			B-13D0086-6B-	2	0
SM98-PS-U40D	UV curable acrylate	400 ± 15 μm	B-13D0086-6B-	3	0
SM98-PS-U40D-H			B-13D0086-6B-	4	0
SM98-PS-U25D		245 ± 15 μm	B-13D0086-6B-	5	0
SM98-PS-U25D-H			B-13D0086-6B-	6	0

\*2% proof test type is available, and code '-H' is added at the end of the product name. (e.g. SM15-PS-U40D-H)



Optical Fiber Division  
1440, Mutsuzaki, Sakura, Chiba 285-8550, Japan

<http://www.fujikura.co.jp/>  
[optodevice@jp.fujikura.com](mailto:optodevice@jp.fujikura.com)

Specifications are subject to change without prior notice